



LianGang Chem

Pigment Red 179 S-0610M for Coatings

High Performance Perylene Pigments Producer in China

Pigment Red 179 (S-0610M) is a high performance perylene pigments, which is widely used in automobile varnish and refinishing paint, plastics, inks and other industrial paint. it has strong light fastness and heat resistance, and the color strength is also very high.

Chemicals Product

Trade Name	Pigment Red 179
C.I. No.	C.I.71130
CAS No.	5521-31-3
EC No.	226-866-1
Molecular Formula	C₂₆H₂₄N₂O₄

Physical Data

Physical State	Powder
Appearance	Amaranthine powder
Odor	Odorless
Molecular Weight	418.42
PH Value	5-7
Light Fastness	7-8
Heat Resistance	200°C
Strength %	100±5
Moisture %	≤0.5
Density	1.51g/cm3

Regulatory Compliance

RoHS FDA Phthalate AP(89)1 SVHC

Applications

Automobile Varnish	●
Refinishing Paint	●
Printing Ink	○
Plastic	○
● recommended	○ limited suitability

Industrial Park 鸿港化工

Liaoning HongGang Chemicals Co., Ltd

No.6, Wanhe Er Road, Aromatic Base, Liaoyang City, Liaoning Prov, China


Tel:0419-7675988 Fax:0419-7675289

E-mail: Lyns3322@163.com Sales@liangangchem.com

www.liangangchem.com

Partical Size

D(v, 0.5): 17.03 μm D[4, 3]: 17.17 μm D[3, 2]: 11.01 μm Obscuration: 19
 SSA: 0.20 m²/g Particle RI: 2.520+0.100 Medium RI: 1.333 Span: 1.22




BET Surface Area

序号	Pd	Pcd	P/Po	V	1/[V(Po/P-1)]
2	12.54606	6.43742	0.06278	6.84472	0.00979
3	16.16254	10.17160	0.09920	7.47412	0.01473
4	19.81961	13.90579	0.13562	7.95185	0.01973
5	23.47668	17.61563	0.17180	8.39854	0.02470
6	27.10939	21.30111	0.20774	8.81420	0.02975
7	31.29412	25.18141	0.24558	9.24666	0.03520
8	35.17848	29.06172	0.28342	9.68711	0.04083
9	39.05473	32.94203	0.32127	10.11957	0.04677

斜率	截距	Vm	C	Cc
0.14375	0.00017	6.94854	848.67382	0.99971

比表面积(m²/g): 30.29563

ARCD



Industrial Park 鸿港化工

Liaoning HongGang Chemicals Co., Ltd

No.6, Wanhe Er Road, Aromatic Base, Liaoyang City, Liaoning Prov, China

Tel:0419-7675988 Fax:0419-7675289

E-mail: Lyns3322@163.com Sales@liangangchem.com

www.liangangchem.com